

## Superior Landscape Fabric

Spunbond Polypropylene Weed Barrier

### DATA SHEET

| <u>TYPICAL PROPERTIES</u>            | <u>TEST METHOD</u> | <u>MIN VALUE</u>                            |
|--------------------------------------|--------------------|---|
| Type                                 |                    | Continuous Filament                         |
| Material                             |                    | Spunbond Polypropylene                      |
| Weight (OZ/SY)                       | ASTMD-3776         | 3.5   |
| Tensile Strength (LBS)               | ASTMD-4632         | 135   |
| Grab Elongation                      | ASTMD-4632         | 70%   |
| Burst (PSI)                          | ASTMD-3786         | 140   |
| Trapezoid Tear (LBS)                 | ASTMD-4533         | 67  |
| Puncture (LBS)                       | ASTMD-4833         | 45.1  |
| Water Permeability<br>(GAL/MIN/SF)   | ASTMD-4491         | 225   |
| UV Exposure<br>(% Strength Retained) | ASTMD-4355         | >70%After 1200 Hours<br>Carbon ARC Exposure |

The Above Properties Are Typical Averages

This Data Supersedes All Previously Issued Data Sheets